



PLATINUM
FIBRE

FABUFILL

CEILING AND WALL INSULATION



TECHNICAL PRODUCT DATASHEETS



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET



FABUFILL POLYESTER INSULATION



011 421 0933 | info@platinumfibre.com | www.platinumfibre.com



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

DESCRIPTION

Thermally Bonded Polyester Insulation

Platinum Fibre's Fabufill polyester insulation is a versatile, easy to install, flexible, strong, lightweight blanket and is manufactured from recycled PET (polyethylene terephthalate) plastic bottles. Produced in a range of different thickness to provide a myriad of thermal and acoustic performances. This non-allergenic, non-irritant and resilient insulation does not support the spread of flame, (Class B/B1/2 fire rating) and is the only polyester insulation available in the marketplace with the SABS mark.

Used in roofs, ceilings, partitions and walls and is manufactured in widths to suit standard spacings of studs, ceiling and floor joists.

After its use, Fabufill's polyester insulation can be easily recycled, making this the perfect 'cradle to grave' insulation product.

MATERIAL DATA

Thickness (mm):	Minimum 40mm (Allow up to 30 days for full recovery of loft).
Roll dimensions (l x w):	10.0 (l) x 0.60 OR 0.75 OR 1.2 (w) metres (tolerance +25mm and -10mm).
Density:	10.1 kg/m ³ (determined in accordance with ASTM C167).
Weight:	400 gm/m ² (tolerance +/- 10%).
Fibre composition:	80% recycled PET (locally sourced) & 20% virgin LMF.

APPLICATIONS



PERFORMANCE

R-Value:	0.77 - 0.96 m ² .K/W (determined in accordance with ASTM C517).
Fire:	B/B1/2/H (determined in accordance with SANS 428) Non-Flammable. Will not contribute to the spreading of flame and will self-extinguish when a heat source is removed.
Combustibility Data:	Combustible at over 750 degrees (determined in accordance with SANS 10177-8).

40mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

STANDARDS & ACCREDITATIONS

SABS Mark: SABS approved to SANS 1381-1:2007 Materials for Thermal Insulation of Buildings | Part 1: Fibre Thermal Insulation Mats.

Permit Number: 9486/15037.

TIPSASA: TIPSASA focuses on the Thermal Insulation Industry with particular emphasis on energy efficient products and systems.

ENVIRONMENTAL

Ozone depleting substances: Does not contain and did not produce any during production. No VOC's are used during the production of this material.

Recycling: 1 ton of Fabufill's polyester insulation is manufactured from approximately 38 000 recycled bottles.

The plastic bags used for transporting the material are made from virgin LDPE material and is 100% recyclable, Grade 4. The inks used in the packaging are food grade.

SPECIFICATION CLAUSE

Clause: Fabufill thermally bonded polyester insulation Roll, thermal and acoustic insulation installed between trusses, joists, studs or above suspended ceilings, SABS approved to SANS 1381-1:2007, non-combustible to SANS 10177-8 and B/B1/2/H to SANS 428. Compression packed.

HANDLING & STORAGE

Safety Precautions: No particular hazards are known. The polyester fibres are not known to cause allergies. With correct use of this product no detrimental effects on health have been recorded.

Transportation: The rolls are compressed into plastic bags and is classified as non-hazardous.

Storage: Rolls to be stored under cover, laid horizontally and stacked no more than 10 units high. Rolls should be kept dry and must not be exposed to a naked flame or any other ignition source.

40mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

INSTALLATION GUIDELINES

Installation tools: Fabufill polyester insulation can be easily torn or cut with a pair of industrial scissors or shears.

Installation methods: Lay loose on ceiling board or suspended between trusses with restraining wires at 300mm intervals.

The distance between roof trusses, ceiling joists and walls studs should be measured, and the appropriate roll widths used.

Fabufill rolls should be installed between the members and the ends of the rolls should be carefully butted or lapped to ensure that the insulation is continuous.

A 50mm gap should be created around downlighters, recessed lights, flue pipes or any low heat sources.

OTHER INFORMATION:

Durability: Fabufill does not physically deteriorate over time and does not require any maintenance. Properties are such that the material will not be damaged during normal handling and installations.

Fungal Attack: Fabufill has good resistance to bacteria, fungi and mildew, and fibre-devouring insects will not damage Fabufill polyester insulation since it is indigestible (tested in accordance with SANS 5484.)

Moisture Absorption: 0.78% (SANS 1381-1:2013 allows up to 2%)

SANS
APPROVED

40mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

DESCRIPTION

Thermally Bonded Polyester Insulation

Platinum Fibre's Fabufill polyester insulation is a versatile, easy to install, flexible, strong, lightweight blanket and is manufactured from recycled PET (polyethylene terephthalate) plastic bottles. Produced in a range of different thickness to provide a myriad of thermal and acoustic performances. This non-allergenic, non-irritant and resilient insulation does not support the spread of flame, (Class B/B1/2 fire rating) and is the only polyester insulation available in the marketplace with the SABS mark.

Used in roofs, ceilings, partitions and walls and is manufactured in widths to suit standard spacings of studs, ceiling and floor joists.

After its use, Fabufill's polyester insulation can be easily recycled, making this the perfect 'cradle to grave' insulation product.

MATERIAL DATA

Thickness (mm):	Minimum 50mm (Allow up to 30 days for full recovery of loft).
Roll dimensions (l x w):	10.0 (l) x 0.60 OR 0.75 OR 1.2 (w) metres (tolerance +25mm and -10mm).
Density:	10.1 kg/m ³ (determined in accordance with ASTM C167).
Weight:	500 gm/m ² (tolerance +/- 10%).
Fibre composition:	80% recycled PET (locally sourced) & 20% virgin LMF.

APPLICATIONS



PERFORMANCE

R-Value:	0.90 – 1.15 m ² .K/W (determined in accordance with ASTM C517).
Fire:	B/B1/2/H (determined in accordance with SANS 428) Non-Flammable. Will not contribute to the spreading of flame and will self-extinguish when a heat source is removed.
Combustibility Data:	Combustible at over 750 degrees (determined in accordance with SANS 10177-8).

50mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

STANDARDS & ACCREDITATIONS

SABS Mark: SABS approved to SANS 1381-1:2007 Materials for Thermal Insulation of Buildings | Part 1: Fibre Thermal Insulation Mats.

Permit Number: 9486/15037.

TIPSASA: TIPSASA focuses on the Thermal Insulation Industry with particular emphasis on energy efficient products and systems.

ENVIRONMENTAL

Ozone depleting substances: Does not contain and did not produce any during production. No VOC's are used during the production of this material.

Recycling: 1 ton of Fabufill's polyester insulation is manufactured from approximately 38 000 recycled bottles.

The plastic bags used for transporting the material are made from virgin LDPE material and is 100% recyclable, Grade 4. The inks used in the packaging are food grade.

SPECIFICATION CLAUSE

Clause: Fabufill thermally bonded polyester insulation Roll, thermal and acoustic insulation installed between trusses, joists, studs or above suspended ceilings, SABS approved to SANS 1381-1:2007, non-combustible to SANS 10177-8 and B/B1/2/H to SANS 428. Compression packed.

HANDLING & STORAGE

Safety Precautions: No particular hazards are known. The polyester fibres are not known to cause allergies. With correct use of this product no detrimental effects on health have been recorded.

Transportation: The rolls are compressed into plastic bags and is classified as non-hazardous.

Storage: Rolls to be stored under cover, laid horizontally and stacked no more than 10 units high. Rolls should be kept dry and must not be exposed to a naked flame or any other ignition source.

50mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

INSTALLATION GUIDELINES

Installation tools: Fabufill polyester insulation can be easily torn or cut with a pair of industrial scissors or shears.

Installation methods: Lay loose on ceiling board or suspended between trusses with restraining wires at 300mm intervals.

The distance between roof trusses, ceiling joists and walls studs should be measured, and the appropriate roll widths used.

Fabufill rolls should be installed between the members and the ends of the rolls should be carefully butted or lapped to ensure that the insulation is continuous.

A 50mm gap should be created around downlighters, recessed lights, flue pipes or any low heat sources.

OTHER INFORMATION:

Durability: Fabufill does not physically deteriorate over time and does not require any maintenance. Properties are such that the material will not be damaged during normal handling and installations.

Fungal Attack: Fabufill has good resistance to bacteria, fungi and mildew, and fibre-devouring insects will not damage Fabufill polyester insulation since it is indigestible (tested in accordance with SANS 5484.)

Moisture Absorption: 0.78% (SANS 1381-1:2013 allows up to 2%)

SANS
APPROVED

50mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

DESCRIPTION

Thermally Bonded Polyester Insulation

Platinum Fibre's Fabufill polyester insulation is a versatile, easy to install, flexible, strong, lightweight blanket and is manufactured from recycled PET (polyethylene terephthalate) plastic bottles. Produced in a range of different thickness to provide a myriad of thermal and acoustic performances. This non-allergenic, non-irritant and resilient insulation does not support the spread of flame, (Class B/B1/2 fire rating) and is the only polyester insulation available in the marketplace with the SABS mark.

Used in roofs, ceilings, partitions and walls and is manufactured in widths to suit standard spacings of studs, ceiling and floor joists.

After its use, Fabufill's polyester insulation can be easily recycled, making this the perfect 'cradle to grave' insulation product.

MATERIAL DATA

Thickness (mm):	Minimum 75mm (Allow up to 30 days for full recovery of loft).
Roll dimensions (l x w):	10.0 (l) x 0.60 OR 0.75 OR 1.2 (w) metres (tolerance +25mm and -10mm).
Density:	10.1 kg/m ³ (determined in accordance with ASTM C167).
Weight:	750 gm/m ² (tolerance +/- 10%).
Fibre composition:	80% recycled PET (locally sourced) & 20% virgin LMF.

APPLICATIONS

A P



roof



ceiling



partition



wall

R O W E D

PERFORMANCE

R-Value:	1.42 – 1.69 m ² .K/W (determined in accordance with ASTM C517).
Fire:	B/B1/2/H (determined in accordance with SANS 428) Non-Flammable. Will not contribute to the spreading of flame and will self-extinguish when a heat source is removed.
Combustibility Data:	Combustible at over 750 degrees (determined in accordance with SANS 10177-8).

75mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

STANDARDS & ACCREDITATIONS

SABS Mark: SABS approved to SANS 1381-1:2007 Materials for Thermal Insulation of Buildings | Part 1: Fibre Thermal Insulation Mats.

Permit Number: 9486/15037.

TIPSASA: TIPSASA focuses on the Thermal Insulation Industry with particular emphasis on energy efficient products and systems.

ENVIRONMENTAL

Ozone depleting substances: Does not contain and did not produce any during production. No VOC's are used during the production of this material.

Recycling: 1 ton of Fabufill's polyester insulation is manufactured from approximately 38 000 recycled bottles.

The plastic bags used for transporting the material are made from virgin LDPE material and is 100% recyclable, Grade 4. The inks used in the packaging are food grade.

SPECIFICATION CLAUSE

Clause: Fabufill thermally bonded polyester insulation Roll, thermal and acoustic insulation installed between trusses, joists, studs or above suspended ceilings, SABS approved to SANS 1381-1:2007, non-combustible to SANS 10177-8 and B/B1/2/H to SANS 428. Compression packed.

HANDLING & STORAGE

Safety Precautions: No particular hazards are known. The polyester fibres are not known to cause allergies. With correct use of this product no detrimental effects on health have been recorded.

Transportation: The rolls are compressed into plastic bags and is classified as non-hazardous.

Storage: Rolls to be stored under cover, laid horizontally and stacked no more than 10 units high. Rolls should be kept dry and must not be exposed to a naked flame or any other ignition source.

75mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

INSTALLATION GUIDELINES

Installation tools: Fabufill polyester insulation can be easily torn or cut with a pair of industrial scissors or shears.

Installation methods: Lay loose on ceiling board or suspended between trusses with restraining wires at 300mm intervals.

The distance between roof trusses, ceiling joists and walls studs should be measured, and the appropriate roll widths used.

Fabufill rolls should be installed between the members and the ends of the rolls should be carefully butted or lapped to ensure that the insulation is continuous.

A 50mm gap should be created around downlighters, recessed lights, flue pipes or any low heat sources.

OTHER INFORMATION:

Durability: Fabufill does not physically deteriorate over time and does not require any maintenance. Properties are such that the material will not be damaged during normal handling and installations.

Fungal Attack: Fabufill has good resistance to bacteria, fungi and mildew, and fibre-devouring insects will not damage Fabufill polyester insulation since it is indigestible (tested in accordance with SANS 5484.)

Moisture Absorption: 0.78% (SANS 1381-1:2013 allows up to 2%)

SANS 5484
APPROVED

75mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

DESCRIPTION

Thermally Bonded Polyester Insulation

Platinum Fibre's Fabufill polyester insulation is a versatile, easy to install, flexible, strong, lightweight blanket and is manufactured from recycled PET (polyethylene terephthalate) plastic bottles. Produced in a range of different thickness to provide a myriad of thermal and acoustic performances. This non-allergenic, non-irritant and resilient insulation does not support the spread of flame, (Class B/B1/2 fire rating) and is the only polyester insulation available in the marketplace with the SABS mark.

Used in roofs, ceilings, partitions and walls and is manufactured in widths to suit standard spacings of studs, ceiling and floor joists.

After its use, Fabufill's polyester insulation can be easily recycled, making this the perfect 'cradle to grave' insulation product.

MATERIAL DATA

Thickness (mm):	Minimum 100mm (Allow up to 30 days for full recovery of loft).
Roll dimensions (l x w):	6.0 (l) x 0.60 OR 0.75 OR 1.2 (w) metres (tolerance +25mm and -10mm).
Density:	10.1 kg/m ³ (determined in accordance with ASTM C167).
Weight:	1000 gm/m ² (tolerance +/- 10%).
Fibre composition:	80% recycled PET (locally sourced) & 20% virgin LMF.

APPLICATIONS



PERFORMANCE

R-Value:	1.75 – 2.20 m ² .K/W (determined in accordance with ASTM C517).
Fire:	B/B1/2/H (determined in accordance with SANS 428) Non-Flammable. Will not contribute to the spreading of flame and will self-extinguish when a heat source is removed.
Combustibility Data:	Combustible at over 750 degrees (determined in accordance with SANS 10177-8).

100mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

STANDARDS & ACCREDITATIONS

SABS Mark: SABS approved to SANS 1381-1:2007 Materials for Thermal Insulation of Buildings | Part 1: Fibre Thermal Insulation Mats.

Permit Number: 9486/15037.

TIPSASA: TIPSASA focuses on the Thermal Insulation Industry with particular emphasis on energy efficient products and systems.

ENVIRONMENTAL

Ozone depleting substances: Does not contain and did not produce any during production. No VOC's are used during the production of this material.

Recycling: 1 ton of Fabufill's polyester insulation is manufactured from approximately 38 000 recycled bottles.

The plastic bags used for transporting the material are made from virgin LDPE material and is 100% recyclable, Grade 4. The inks used in the packaging are food grade.

SPECIFICATION CLAUSE

Clause: Fabufill thermally bonded polyester insulation Roll, thermal and acoustic insulation installed between trusses, joists, studs or above suspended ceilings, SABS approved to SANS 1381-1:2007, non-combustible to SANS 10177-8 and B/B1/2/H to SANS 428. Compression packed.

HANDLING & STORAGE

Safety Precautions: No particular hazards are known. The polyester fibres are not known to cause allergies. With correct use of this product no detrimental effects on health have been recorded.

Transportation: The rolls are compressed into plastic bags and is classified as non-hazardous.

Storage: Rolls to be stored under cover, laid horizontally and stacked no more than 10 units high. Rolls should be kept dry and must not be exposed to a naked flame or any other ignition source.

100mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

INSTALLATION GUIDELINES

Installation tools: Fabufill polyester insulation can be easily torn or cut with a pair of industrial scissors or shears.

Installation methods: Lay loose on ceiling board or suspended between trusses with restraining wires at 300mm intervals.

The distance between roof trusses, ceiling joists and walls studs should be measured, and the appropriate roll widths used.

Fabufill rolls should be installed between the members and the ends of the rolls should be carefully butted or lapped to ensure that the insulation is continuous.

A 50mm gap should be created around downlighters, recessed lights, flue pipes or any low heat sources.

OTHER INFORMATION:

Durability: Fabufill does not physically deteriorate over time and does not require any maintenance. Properties are such that the material will not be damaged during normal handling and installations.

Fungal Attack: Fabufill has good resistance to bacteria, fungi and mildew, and fibre-devouring insects will not damage Fabufill polyester insulation since it is indigestible (tested in accordance with SANS 5484.)

Moisture Absorption: 0.78% (SANS 1381-1:2013 allows up to 2%)

SANS
APPROVED

100mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

DESCRIPTION

Thermally Bonded Polyester Insulation

Platinum Fibre's Fabufill polyester insulation is a versatile, easy to install, flexible, strong, lightweight blanket and is manufactured from recycled PET (polyethylene terephthalate) plastic bottles. Produced in a range of different thickness to provide a myriad of thermal and acoustic performances. This non-allergenic, non-irritant and resilient insulation does not support the spread of flame, (Class B/B1/2 fire rating) and is the only polyester insulation available in the marketplace with the SABS mark.

Used in roofs, ceilings, partitions and walls and is manufactured in widths to suit standard spacings of studs, ceiling and floor joists.

After its use, Fabufill's polyester insulation can be easily recycled, making this the perfect 'cradle to grave' insulation product.

MATERIAL DATA

Thickness (mm):	Minimum 135mm (Allow up to 30 days for full recovery of loft).
Roll dimensions (l x w):	5.0 (l) x 0.60 OR 0.75 OR 1.2 (w) metres (tolerance +25mm and -10mm).
Density:	10.1 kg/m ³ (determined in accordance with ASTM C167).
Weight:	1350 gm/m ² (tolerance +/- 10%).
Fibre composition:	80% recycled PET (locally sourced) & 20% virgin LMF.

APPLICATIONS



PERFORMANCE

R-Value:	2.55 – 2.70 m ² .K/W (determined in accordance with ASTM C517).
Fire:	B/B1/2/H (determined in accordance with SANS 428) Non-Flammable. Will not contribute to the spreading of flame and will self-extinguish when a heat source is removed.
Combustibility Data:	Combustible at over 750 degrees (determined in accordance with SANS 10177-8).

135mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

STANDARDS & ACCREDITATIONS

SABS Mark: SABS approved to SANS 1381-1:2007 Materials for Thermal Insulation of Buildings | Part 1: Fibre Thermal Insulation Mats.

Permit Number: 9486/15037.

TIPSASA: TIPSASA focuses on the Thermal Insulation Industry with particular emphasis on energy efficient products and systems.

ENVIRONMENTAL

Ozone depleting substances: Does not contain and did not produce any during production. No VOC's are used during the production of this material.

Recycling: 1 ton of Fabufill's polyester insulation is manufactured from approximately 38 000 recycled bottles.

The plastic bags used for transporting the material are made from virgin LDPE material and is 100% recyclable, Grade 4. The inks used in the packaging are food grade.

SPECIFICATION CLAUSE

Clause: Fabufill thermally bonded polyester insulation Roll, thermal and acoustic insulation installed between trusses, joists, studs or above suspended ceilings, SABS approved to SANS 1381-1:2007, non-combustible to SANS 10177-8 and B/B1/2/H to SANS 428. Compression packed.

HANDLING & STORAGE

Safety Precautions: No particular hazards are known. The polyester fibres are not known to cause allergies. With correct use of this product no detrimental effects on health have been recorded.

Transportation: The rolls are compressed into plastic bags and is classified as non-hazardous.

Storage: Rolls to be stored under cover, laid horizontally and stacked no more than 10 units high. Rolls should be kept dry and must not be exposed to a naked flame or any other ignition source.

135mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

PRODUCT DATASHEET

INSTALLATION GUIDELINES

Installation tools: Fabufill polyester insulation can be easily torn or cut with a pair of industrial scissors or shears.

Installation methods: Lay loose on ceiling board or suspended between trusses with restraining wires at 300mm intervals.

The distance between roof trusses, ceiling joists and walls studs should be measured, and the appropriate roll widths used.

Fabufill rolls should be installed between the members and the ends of the rolls should be carefully butted or lapped to ensure that the insulation is continuous.

A 50mm gap should be created around downlighters, recessed lights, flue pipes or any low heat sources.

OTHER INFORMATION:

Durability: Fabufill does not physically deteriorate over time and does not require any maintenance. Properties are such that the material will not be damaged during normal handling and installations.

Fungal Attack: Fabufill has good resistance to bacteria, fungi and mildew, and fibre-devouring insects will not damage Fabufill polyester insulation since it is indigestible (tested in accordance with SANS 5484.)

Moisture Absorption: 0.78% (SANS 1381-1:2013 allows up to 2%)

SANS
APPROVED

135mm

FABUFILL POLYESTER
INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET



FABUFILL *LITE* POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

DESCRIPTION

Thermally Bonded Polyester Insulation

Platinum Fibre's Fabufill LITE polyester insulation is a versatile, easy to install, flexible, strong, lightweight blanket and is manufactured from recycled PET (polyethylene terephthalate) plastic bottles. Produced in a range of different thickness to provide a myriad of thermal and acoustic performances. This non-allergenic, non-irritant and resilient insulation does not support the spread of flame (Class B/B1/2 fire rating).

Used in roofs, ceilings, partitions and walls and is manufactured in widths to suit standard spacings of studs, ceiling and floor joists.

After its use, Fabufill's LITE polyester insulation can be easily recycled, making this the perfect 'cradle to grave' insulation product.

MATERIAL DATA

Thickness (mm):	Minimum 40mm. (Allow up to 30 days for full recovery of loft).
Roll dimensions (l x w):	10.0 (l) x 0.60 OR 0.75 OR 1.2 (w) metres (tolerance +25mm and -10mm).
Fibre composition:	80% recycled PET (locally sourced) & 20% virgin LMF.

APPLICATIONS



roof



ceiling



partition



wall

PERFORMANCE

R-Value:	0.76 m ² .K/W (determined in accordance with ASTM C517).
Fire:	B/B1/2/H (determined in accordance with SANS 428) Non-Flammable. Will not contribute to the spreading of flame and will self-extinguish when a heat source is removed.
Combustibility Data:	Combustible at over 750 degrees (determined in accordance with SANS 10177-8).

40

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

ENVIRONMENTAL

- Ozone depleting substances:** Does not contain and did not produce any during production. No VOC's are used during the production of this material.
- Recycling:** 1 ton of Fabufill's polyester insulation is manufactured from approximately 38 000 recycled bottles.
- The plastic bags used for transporting the material are made from virgin LDPE material and is 100% recyclable, Grade 4. The inks used in the packaging are food grade.

SPECIFICATION CLAUSE

- Clause:** Fabufill LITE thermally bonded polyester insulation Roll, thermal and acoustic insulation installed between trusses, joists, studs or above suspended ceilings, non-combustible to SANS 10177-8 and B/B1/2/H to SANS 428. Compression packed.

HANDLING & STORAGE

- Safety Precautions:** No particular hazards are known. The polyester fibres are not known to cause allergies. With correct use of this product no detrimental effects on health have been recorded.
- Transportation:** The rolls are compressed into plastic bags and is classified as non-hazardous.
- Storage:** Rolls to be stored under cover, laid horizontally and stacked no more than 10 units high. Rolls should be kept dry and must not be exposed to a naked flame or any other ignition source.

40

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

INSTALLATION GUIDELINES

Installation tools: Fabufill polyester insulation can be easily torn or cut with a pair of industrial scissors or shears.

Installation methods: Lay loose on ceiling board or suspended between trusses with restraining wires at 300mm intervals.

The distance between roof trusses, ceiling joists and walls studs should be measured, and the appropriate roll widths used.

Fabufill rolls should be installed between the members and the ends of the rolls should be carefully butted or lapped to ensure that the insulation is continuous.

A 50mm gap should be created around downlighters, recessed lights, flue pipes or any low heat sources.

OTHER INFORMATION:

Durability: Fabufill does not physically deteriorate over time and does not require any maintenance. Properties are such that the material will not be damaged during normal handling and installations.

Fungal Attack: Fabufill has good resistance to bacteria, fungi and mildew and fibre-devouring insects will not damage Fabufill polyester insulation since it is indigestible (tested in accordance with SANS 5484.)

Moisture Absorption: 0.78% (SANS 1381-1:2013 allows up to 2%)

40

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

DESCRIPTION

Thermally Bonded Polyester Insulation

Platinum Fibre's Fabufill LITE polyester insulation is a versatile, easy to install, flexible, strong, lightweight blanket and is manufactured from recycled PET (polyethylene terephthalate) plastic bottles. Produced in a range of different thickness to provide a myriad of thermal and acoustic performances. This non-allergenic, non-irritant and resilient insulation does not support the spread of flame (Class B/B1/2 fire rating).

Used in roofs, ceilings, partitions and walls and is manufactured in widths to suit standard spacings of studs, ceiling and floor joists.

After its use, Fabufill's LITE polyester insulation can be easily recycled, making this the perfect 'cradle to grave' insulation product.

MATERIAL DATA

Thickness (mm):	Minimum 50mm. (Allow up to 30 days for full recovery of loft).
Roll dimensions (l x w):	10.0 (l) x 0.60 OR 0.75 OR 1.2 (w) metres (tolerance +25mm and -10mm).
Fibre composition:	80% recycled PET (locally sourced) & 20% virgin LMF.

APPLICATIONS



roof



ceiling



partition



wall

PERFORMANCE

R-Value:	0.82 m ² .K/W (determined in accordance with ASTM C517).
Fire:	B/B1/2/H (determined in accordance with SANS 428) Non-Flammable. Will not contribute to the spreading of flame and will self-extinguish when a heat source is removed.
Combustibility Data:	Combustible at over 750 degrees (determined in accordance with SANS 10177-8).

50

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

ENVIRONMENTAL

- Ozone depleting substances:** Does not contain and did not produce any during production. No VOC's are used during the production of this material.
- Recycling:** 1 ton of Fabufill's polyester insulation is manufactured from approximately 38 000 recycled bottles.
- The plastic bags used for transporting the material are made from virgin LDPE material and is 100% recyclable, Grade 4. The inks used in the packaging are food grade.

SPECIFICATION CLAUSE

- Clause:** Fabufill LITE thermally bonded polyester insulation Roll, thermal and acoustic insulation installed between trusses, joists, studs or above suspended ceilings, non-combustible to SANS 10177-8 and B/B1/2/H to SANS 428. Compression packed.

HANDLING & STORAGE

- Safety Precautions:** No particular hazards are known. The polyester fibres are not known to cause allergies. With correct use of this product no detrimental effects on health have been recorded.
- Transportation:** The rolls are compressed into plastic bags and is classified as non-hazardous.
- Storage:** Rolls to be stored under cover, laid horizontally and stacked no more than 10 units high. Rolls should be kept dry and must not be exposed to a naked flame or any other ignition source.

50

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

INSTALLATION GUIDELINES

Installation tools: Fabufill polyester insulation can be easily torn or cut with a pair of industrial scissors or shears.

Installation methods: Lay loose on ceiling board or suspended between trusses with restraining wires at 300mm intervals.

The distance between roof trusses, ceiling joists and walls studs should be measured, and the appropriate roll widths used.

Fabufill rolls should be installed between the members and the ends of the rolls should be carefully butted or lapped to ensure that the insulation is continuous.

A 50mm gap should be created around downlighters, recessed lights, flue pipes or any low heat sources.

OTHER INFORMATION:

Durability: Fabufill does not physically deteriorate over time and does not require any maintenance. Properties are such that the material will not be damaged during normal handling and installations.

Fungal Attack: Fabufill has good resistance to bacteria, fungi and mildew and fibre-devouring insects will not damage Fabufill polyester insulation since it is indigestible (tested in accordance with SANS 5484.)

Moisture Absorption: 0.78% (SANS 1381-1:2013 allows up to 2%)

50

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

DESCRIPTION

Thermally Bonded Polyester Insulation

Platinum Fibre's Fabufill LITE polyester insulation is a versatile, easy to install, flexible, strong, lightweight blanket and is manufactured from recycled PET (polyethylene terephthalate) plastic bottles. Produced in a range of different thickness to provide a myriad of thermal and acoustic performances. This non-allergenic, non-irritant and resilient insulation does not support the spread of flame (Class B/B1/2 fire rating).


Used in roofs, ceilings, partitions and walls and is manufactured in widths to suit standard spacings of studs, ceiling and floor joists.

After its use, Fabufill's LITE polyester insulation can be easily recycled, making this the perfect 'cradle to grave' insulation product.

MATERIAL DATA

Thickness (mm):	Minimum 75mm. (Allow up to 30 days for full recovery of loft).
Roll dimensions (l x w):	8.0 (l) x 0.60 OR 0.75 OR 1.2 (w) metres (tolerance +25mm and -10mm).
Fibre composition:	80% recycled PET (locally sourced) & 20% virgin LMF.

APPLICATIONS



PERFORMANCE

R-Value:	1.37 m ² .K/W (determined in accordance with ASTM C517).
Fire:	B/B1/2/H (determined in accordance with SANS 428) Non-Flammable. Will not contribute to the spreading of flame and will self-extinguish when a heat source is removed.
Combustibility Data:	Combustible at over 750 degrees (determined in accordance with SANS 10177-8).

75

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

ENVIRONMENTAL

- Ozone depleting substances:** Does not contain and did not produce any during production. No VOC's are used during the production of this material.
- Recycling:** 1 ton of Fabufill's polyester insulation is manufactured from approximately 38 000 recycled bottles.
- The plastic bags used for transporting the material are made from virgin LDPE material and is 100% recyclable, Grade 4. The inks used in the packaging are food grade.

SPECIFICATION CLAUSE

- Clause:** Fabufill LITE thermally bonded polyester insulation Roll, thermal and acoustic insulation installed between trusses, joists, studs or above suspended ceilings, non-combustible to SANS 10177-8 and B/B1/2/H to SANS 428. Compression packed.

HANDLING & STORAGE

- Safety Precautions:** No particular hazards are known. The polyester fibres are not known to cause allergies. With correct use of this product no detrimental effects on health have been recorded.
- Transportation:** The rolls are compressed into plastic bags and is classified as non-hazardous.
- Storage:** Rolls to be stored under cover, laid horizontally and stacked no more than 10 units high. Rolls should be kept dry and must not be exposed to a naked flame or any other ignition source.

75

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

INSTALLATION GUIDELINES

Installation tools: Fabufill polyester insulation can be easily torn or cut with a pair of industrial scissors or shears.

Installation methods: Lay loose on ceiling board or suspended between trusses with restraining wires at 300mm intervals.

The distance between roof trusses, ceiling joists and walls studs should be measured, and the appropriate roll widths used.

Fabufill rolls should be installed between the members and the ends of the rolls should be carefully butted or lapped to ensure that the insulation is continuous.

A 50mm gap should be created around downlighters, recessed lights, flue pipes or any low heat sources.

OTHER INFORMATION:

Durability: Fabufill does not physically deteriorate over time and does not require any maintenance. Properties are such that the material will not be damaged during normal handling and installations.

Fungal Attack: Fabufill has good resistance to bacteria, fungi and mildew and fibre-devouring insects will not damage Fabufill polyester insulation since it is indigestible (tested in accordance with SANS 5484.)

Moisture Absorption: 0.78% (SANS 1381-1:2013 allows up to 2%)

75

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

DESCRIPTION

Thermally Bonded Polyester Insulation

Platinum Fibre's Fabufill LITE polyester insulation is a versatile, easy to install, flexible, strong, lightweight blanket and is manufactured from recycled PET (polyethylene terephthalate) plastic bottles. Produced in a range of different thickness to provide a myriad of thermal and acoustic performances. This non-allergenic, non-irritant and resilient insulation does not support the spread of flame (Class B/B1/2 fire rating).


Used in roofs, ceilings, partitions and walls and is manufactured in widths to suit standard spacings of studs, ceiling and floor joists.

After its use, Fabufill's LITE polyester insulation can be easily recycled, making this the perfect 'cradle to grave' insulation product.

MATERIAL DATA

Thickness (mm):	Minimum 100mm. (Allow up to 30 days for full recovery of loft).
Roll dimensions (l x w):	6.0 (l) x 0.60 OR 0.75 OR 1.2 (w) metres (tolerance +25mm and -10mm).
Fibre composition:	80% recycled PET (locally sourced) & 20% virgin LMF.

APPLICATIONS



PERFORMANCE

R-Value:	1.65 m ² .K/W (determined in accordance with ASTM C517).
Fire:	B/B1/2/H (determined in accordance with SANS 428) Non-Flammable. Will not contribute to the spreading of flame and will self-extinguish when a heat source is removed.
Combustibility Data:	Combustible at over 750 degrees (determined in accordance with SANS 10177-8).

100

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

ENVIRONMENTAL

- Ozone depleting substances:** Does not contain and did not produce any during production. No VOC's are used during the production of this material.
- Recycling:** 1 ton of Fabufill's polyester insulation is manufactured from approximately 38 000 recycled bottles.
- The plastic bags used for transporting the material are made from virgin LDPE material and is 100% recyclable, Grade 4. The inks used in the packaging are food grade.

SPECIFICATION CLAUSE

- Clause:** Fabufill LITE thermally bonded polyester insulation Roll, thermal and acoustic insulation installed between trusses, joists, studs or above suspended ceilings, non-combustible to SANS 10177-8 and B/B1/2/H to SANS 428. Compression packed.

HANDLING & STORAGE

- Safety Precautions:** No particular hazards are known. The polyester fibres are not known to cause allergies. With correct use of this product no detrimental effects on health have been recorded.
- Transportation:** The rolls are compressed into plastic bags and is classified as non-hazardous.
- Storage:** Rolls to be stored under cover, laid horizontally and stacked no more than 10 units high. Rolls should be kept dry and must not be exposed to a naked flame or any other ignition source.

100

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

INSTALLATION GUIDELINES

Installation tools: Fabufill polyester insulation can be easily torn or cut with a pair of industrial scissors or shears.

Installation methods: Lay loose on ceiling board or suspended between trusses with restraining wires at 300mm intervals.

The distance between roof trusses, ceiling joists and walls studs should be measured, and the appropriate roll widths used.

Fabufill rolls should be installed between the members and the ends of the rolls should be carefully butted or lapped to ensure that the insulation is continuous.

A 50mm gap should be created around downlighters, recessed lights, flue pipes or any low heat sources.

OTHER INFORMATION:

Durability: Fabufill does not physically deteriorate over time and does not require any maintenance. Properties are such that the material will not be damaged during normal handling and installations.

Fungal Attack: Fabufill has good resistance to bacteria, fungi and mildew and fibre-devouring insects will not damage Fabufill polyester insulation since it is indigestible (tested in accordance with SANS 5484.)

Moisture Absorption: 0.78% (SANS 1381-1:2013 allows up to 2%)

100

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

DESCRIPTION

Thermally Bonded Polyester Insulation

Platinum Fibre's Fabufill LITE polyester insulation is a versatile, easy to install, flexible, strong, lightweight blanket and is manufactured from recycled PET (polyethylene terephthalate) plastic bottles. Produced in a range of different thickness to provide a myriad of thermal and acoustic performances. This non-allergenic, non-irritant and resilient insulation does not support the spread of flame (Class B/B1/2 fire rating).


Used in roofs, ceilings, partitions and walls and is manufactured in widths to suit standard spacings of studs, ceiling and floor joists.

After its use, Fabufill's LITE polyester insulation can be easily recycled, making this the perfect 'cradle to grave' insulation product.

MATERIAL DATA

Thickness (mm):	Minimum 130mm. (Allow up to 30 days for full recovery of loft).
Roll dimensions (l x w):	5.0 (l) x 0.60 OR 0.75 OR 1.2 (w) metres (tolerance +25mm and -10mm).
Fibre composition:	80% recycled PET (locally sourced) & 20% virgin LMF.

APPLICATIONS



PERFORMANCE

R-Value:	2.06 m ² .K/W (determined in accordance with ASTM C517).
Fire:	B/B1/2/H (determined in accordance with SANS 428) Non-Flammable. Will not contribute to the spreading of flame and will self-extinguish when a heat source is removed.
Combustibility Data:	Combustible at over 750 degrees (determined in accordance with SANS 10177-8).

130

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

ENVIRONMENTAL

- Ozone depleting substances:** Does not contain and did not produce any during production. No VOC's are used during the production of this material.
- Recycling:** 1 ton of Fabufill's polyester insulation is manufactured from approximately 38 000 recycled bottles.
- The plastic bags used for transporting the material are made from virgin LDPE material and is 100% recyclable, Grade 4. The inks used in the packaging are food grade.

SPECIFICATION CLAUSE

- Clause:** Fabufill LITE thermally bonded polyester insulation Roll, thermal and acoustic insulation installed between trusses, joists, studs or above suspended ceilings, non-combustible to SANS 10177-8 and B/B1/2/H to SANS 428. Compression packed.

HANDLING & STORAGE

- Safety Precautions:** No particular hazards are known. The polyester fibres are not known to cause allergies. With correct use of this product no detrimental effects on health have been recorded.
- Transportation:** The rolls are compressed into plastic bags and is classified as non-hazardous.
- Storage:** Rolls to be stored under cover, laid horizontally and stacked no more than 10 units high. Rolls should be kept dry and must not be exposed to a naked flame or any other ignition source.

130

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

LITE PRODUCT DATASHEET

INSTALLATION GUIDELINES

Installation tools: Fabufill polyester insulation can be easily torn or cut with a pair of industrial scissors or shears.

Installation methods: Lay loose on ceiling board or suspended between trusses with restraining wires at 300mm intervals.

The distance between roof trusses, ceiling joists and walls studs should be measured, and the appropriate roll widths used.

Fabufill rolls should be installed between the members and the ends of the rolls should be carefully butted or lapped to ensure that the insulation is continuous.

A 50mm gap should be created around downlighters, recessed lights, flue pipes or any low heat sources.

OTHER INFORMATION:

Durability: Fabufill does not physically deteriorate over time and does not require any maintenance. Properties are such that the material will not be damaged during normal handling and installations.

Fungal Attack: Fabufill has good resistance to bacteria, fungi and mildew and fibre-devouring insects will not damage Fabufill polyester insulation since it is indigestible (tested in accordance with SANS 5484.)

Moisture Absorption: 0.78% (SANS 1381-1:2013 allows up to 2%)

130

FABUFILL *LITE*
POLYESTER INSULATION



PLATINUM
FIBRE

FABUFILL

CEILING AND WALL INSULATION

CONTACT:

t: 011 421 0933

m: info@platinumfibre.com

w: www.platinumfibre.com

Platinum Fibre provides all information contained in this publication based on data available at the time and reserves the right to amend such information from time to time.